Record Group 104. Entry 28.

Register of Ingots Fine Gold & Toughened Bars. 1867-1870.

Digitized October 18, 2023, Philadelphia, Pennsylvania.
Box 7, Book 23, for 1867-70.

Note: Lightly printed and written text may be difficult to read in scanned version. Hidden words might be visible on the original pages. Larger (18+ inch) documents are scanned in multiple parts. Correspondence organization is presented as stored and is not always in chronological order.

RG 104 RECORDS OF THE BUREAU OF THE MINT

Records of the U.S. Mint at Philadelphia
Deposit Record of the Assays

ASSAY WORKBOOK, 1795-1905

Box 07 NC-152 Entry 28

Register of —

...ools, Fine Gold Bars,

&

Toughened Bars.

WILLIAM PENN
48

Register of Ingots, Fine Gold Bars and Toughened Bars

March 25th 1867

Ingots.

54 - 900.1 } 6 - 900 } 4
55 - 900.3 } 6 - 900.2 } 4
56 - 900.1 } 6 - 900. } 4
57 - 900.2 } 6 - 900.1 } 4

Fine Gold Bar

30 - 998.4)6 - 998.4)6

March 27th 1867

Ingots

58 - 899.9 } 5 - 899.9 } 4
59 - 900. } 5 - " } 4

Fine Gold Bar

31 - 998.4)5 - 998.3)5

March 28th 1867

Fine Gold Bar

32 - 998.3)5 - 998.4)6

April 1st 1867

F. G. Bar.

33 - 998.1)5 - 998.2)4

April 4th 1867

F. G. Bar.

34 - 998.3)5 - 998.2)6

April 2nd 1867

Standard Bar from Slip

1 - 900)5 - 899.9)4

Toughened & fine slips. (stand).

1 - 898.1)5 - 898)6

April 12th 1867

F. G. Bars

35 - 998.8 } 6 - 998.7
36 - 998.5 } 6 - 998.6 } 7

Ingots.

60 - 900.1 } 6 - 900.3 } 6
1 - 900.2 } 6 - 900. } 6
2 - 900.2 } 6 - 900.3 } 6
3 - 900.2 } 6 - 900.2 } 6
4 -

April 13th 1867

Toughened Bars

12 - 992. } 6 - 992. } 7

April 17th 1867

F. G. Bar.

37 - 998.4 } 5 - 998.5 } 7

April 18th 1867

Ingots

64 - 900 } 6 - 899.9 } 5
65 - 899.8 } 5 - 899.8 } 5
66 - 899.7 } 6 - 899.9 } 5

April 20th 1867

Toughened Bars.

13 - 994.2 } 7 - 994.2 } 6
14 - 994.1 } 7 - 994. } 6

April 22nd 1867

F. G. Bar

38. - 998.4 } 6 - 998.3 } 5

April 24th 1867

Ingots

67 - 900.3 } 5 - 900.2 } 6
68 - 900. } 5 - 899.8 } 6
69 - 899.8 } 6 - 900 } 6

April 26th 1867

Toughened Bar

15 - 983 } 7 - 983 } 6

F. G. Bar

39 - 998.5 } 7 - 998.5 } 6

April 29th 1867

F. G. Bar

40 - 998.4 } 6 - 998.4 } 5

May 3rd 1867.
Fine Gold Bar

41 - 998.4)7 - 998.5)6

May 7th 1867
Fine Gold Bars.

42 - 998.9 } 9 - 998.9 } 8
3 - 998.9 } 9 - 998.8 } 8
4 - 998.9 } 9 - 998.8 } 8
5 - 998.8 } 9 - 998.8 } 8

May 8th 1867
Fine Gold Bars

46 - 998.9 } 9 998.9 } 9
47 - 998.9 } 9 998.7 } 9
48 - 998.9 } 9 998.9 } 9
49 - 998.9 } 9 998.9 } 9

May 9th 1867.
Fine Gold Bar

50 - 998.8)6 - 998.7)6

May 11th 1867
Toughened Bars.

16 - 993.3 } 7 - 993.2 } 7
17 - 993. } 7 - 993. } 7

May 14th 1867
Fine Gold Bar

51 - 998.9)7 - 998.9)8

May 16th 1867
Ingots.

1 - 900 } 9 - 899.7 } 8
2 - 898.2 } 9 - 899.8 } 8
3 - 899.2 } 9 - 899.9 } 8

May 17th 1867
Fine Gold Bars

52 - 998.9 } 8 - 998.8 } 8
3 - 998.8 } 8 - 998.6 } 8
4 - 998.8 } 8 - 998.6 } 8

May 24th 1867
Fine Gold Bar

55 - 998.7)6 - 998.7)8

Ingots

74 - 899.9 } 5 - 899.9 } 6
75 - 899.8 } 5 - 899.7 } 6
76 - 899.6 } 5 - 899.7 } 6

May 27th 1867
Fine Gold Bar
56 - 998.9)8 - 998.9)7

May 28th 1867
Fine Gold Bar
57 - 998.9)8 - 998.8)7

May 29th 1867
Fine Gold Bar
58 - 999.1)9 - 999.1)10

May 30th 1867
Fine Gold Bar
59 - 998.9)8 - 999)8

May 31st 1867
Fine Gold Bars.
60 - 998.6)7 -
61 - 998.8)7 - 998.8)

June 1st 1867
Fine Gold Bar
62 - 998.8)7 - 999)

June 4th 1867
Fine Gold Bar
63 - 998.8)7 - 998.9)7

June 5th 1867
64 - 998.9)9 - 999)

June 6th 1867
Fine Gold Ingot.
No. 1 - 996.1)8 - 996.)8

June 10th 1867
Fine Gold Bar
65 - 998.8)7 - 998.7)7

June 11th 1867.
Fine Gold Bar
66. —997.6)9 —997.5)8

Ingots.
77 -899.9} -900 }5
78 -899.9} -899.7 }5

June 12th 1867
Fine Gold Bar
67 -996.)8 -995.7)7

June 14th 1867
Fine Gold Bars.
68 -995.6} -995.8}6
69 -995.7} -996.0 (

June 15th 1867
Fine Gold Bar
70 -995.8 }8 -996.4

toughened bar
18 -994.2)8 -994.)

June 19th 1867
Fine Gold Bar
71 -996.)8 -996.2)

June 22nd 1867
Fine Gold Bars.
72 -995.8} -995.8}9
73 -995.9} -996 }9

June 24th 1867
Fine Gold Bar
74 -993.4)7 -993.5
R. M
74 -995.8)7 -995.6)

June 25th 1867
Fine Gold Bar
75 -995.6) -995.4

July 1st 1867
F. G. Bar
76 – 996.1 }8 – 995.8

80 – 899.9 } 8 – 900 } 7
81 – 900.3 } 8 – 900.2 } 7
82 – 900.2 – 900.2

July 3rd 1867.
F. G. Bars
77 – 995.9 } 8 – 995.9
78 – 995.7 } 8 – 995.6

July 13th 1867.
Ingots.
83 – 899.8 } 7 – 900. } 8
84 – 899.9 } 7 – 900.3 } 8
85 – 899.8 – 899.8

July 5th 1867
F. G. Bar
79 – 995.7 }5 – 995.7

Fine Gold Bars.
80 – 996.2 } 10 – 996.5 } 10.
81 – 996.2 } 10 – 996. } 10.
82 – 996.3 } 10 – 996.3 } 10.
83 – 996.3 } 10 – 996.2 } 10.

July 12th 1867
Toughened Bars.
19 – 994.2 } 9 – 993.8 } 8
20 – 994.6 } 9 – 993.9 } 8
Ingots.
79 – 900 } – 899.8

July 16th 1867
Fine Gold Bar
84 – 995.9 }1 – 99.6 }
Ingots.

86 – 900.5 } – 900.5 }
87 – 900.1 } 6 – 900. } 5
88 – 899.9 } – 899.8 }

Ingots.

92 – 900.1 } – 900 }
93 – 899.9 } 7 – 900 } 8
94 – 900.1 } – 900 }

July 18th 1867
Ingots.

89 – 900.1 } – 899.8 }
90 – 899.9 } 7 – 899.8 } 3
91 – 900.1 } – 899.8 }

July 19th 1867
Fine Gold Ingot,
No. 2 – 998.7)8 – 998.7)8
Fine Gold Bar
85 – 996.2)8 – 996.2)8

July 21st 1867
Fine Gold Bar
86 – 995.8)6 – 996.1)8

July 27th 1867
F. G. Bars
87 – 996 } – 995.8 }
88 – 996 } – 995.9 } 7

July 29th 1867
Toughened Bars
21 – 992.5)11 – 992.4)10

July 30th 1867
Toughened Bars.
22 – 987.3)6 – 987.1)

July 31st 1867.
Fine Gold Bar
89 - 997.5 | 89 - 998.1 | 7

August 1st 1867
F. G. Bar
90 - 998.5 | - 998.5 | 8

August 2nd 1867
F. G. Bar
91 - 998.7 | - 998.3 | 5
Aug 8th F G Bar
92 998.5 998.3
93 998.5 998.2 7
Aug 10th
94 998 998
95 997.9 997.7 3

Thursday Aug 15th
Fine Gold Bar
96 - 998.5 | 6 - 998.6 | 9
Ingots.
95 - 899.7 | - 899.7
96 - 899.7 | - 900.3
97 - 899.8 | 4 - 900.4 | 5
98 - 885.5 | - 887.
99 - 899.8 | - 900.5
95 - 900.2
96 - 900.6
97 - 900.3 | 8
98 - 886.5
99 - 900.6

August 19th 1867
F. G. Bar
97 - 998.4 | 6 - 998.3 | 5

August 22nd 1867
Fine G. Bar
98 – 998.3)5 – 998.6)Dft

August 23rd 1867
Fine G. Bar
99 – 998.7)9 – 998.6)

August 26th 1867
Fine G. Bar
100 – 998.5)7 – 998.4)7

August 29th 1867.
Fine Gold Bar
101 – 998.9)13 – 998.8)9

August 31st 1867
Fine G. Bars.
102 – 998.5)9 – 998.4)9
103 – 998.6) – 998.6)

September 3rd 1867
F. G. Bar
104 – 998.3)5 – 998.3)5

September 5th 1867
F. G. Bars
105 – 998.7)9 – 998.7)9
106 – 998.6) – 998.7)

September 6th 1867
F. G. Bar
107 – 998.8)9 – 998.8)8

September 7th 1867
F. G. Bar
108 – 998.7)9 – 998.5)8

September 11th 1867
F. G. Bar.
109 – 998.5)2 – 998.4)6

September 11th 1867.

Ingots.

100 - 902.2 } - 901 }
101 - 901. } - 900,9 } 6
102 - 877.2 } - 877,8 } 11
103 - 847.4 } - 847,8 }
100 - 900.1 } 5 - 900 } 4
101 - 900.1 } 900 }

Fine G. Bars

110 - 998.3 } - 998.4 }
111 - 998.6 } 7 - 998.7 } 7

September 12th 1867

F. Gold Bar

112 - 998.6) 7 - 999.)

September 17th 1867.

F. G. Bar

113 - 998.4) 6 - 998.7)

September 19th 1867

F. G. Bar.

114 - 998.7) 7 - 999.) 10 - 998.8)

September 20th 1867

F. G. Bar

115 - 998.6) 8 - 999)

September 25th 1867

F. G. Bar.

116 - 998.5) 8 - 998.5)

Ingots.

104 - 899.3 } - 899.5 }
5 - 900.4 } 10 - 900.5 } 11
6 - 900.5 } - 900.5 }

Sept. 26th

7 - 901.2 } 15 - 901.3 } 11
8 - 900.9 } - 901. }

F. G. Bar.

117 - 998.9) 11 - 998.8)

September 27th 1867

Ingots.

R.A.

107 – 900.7 } 9 – 900.8 } 10
108 – 900.3 } 9 – 900.5 } 10

Toughened bars.

23 – 994.3 } 4 – 994.7 }
24 – 994.2 } 4 – 993.8 }
24 – 994.3 } 5 – 994.4 } 15

October 2nd 1867.

F. G. Bar

118 – 998.5 } 5 – 998.5 } 6

Ingots.

109 – 900.4 } 10 – 899.7 } 10
10 – 903.6 } 10 – 902.7 } 10
11 – 900.5 } 10 – 900.3 } 10
12 – 900.7 } 10 – 900.5 } 10
13 – 900.5 } 10 – 900.4 } 10

October 3rd 1867.

Ingots –

109 – 901.1 } 10 – 901 } 10
10 – 903.2 } 10 – 903 } 10
14 – 901.5 } 10 – 901.3 } 10
15 – 901. } 10 – 901.4 } 10
16 – 901.3 } 10 – 901. } 10

F.G Bar

119 – 999.4 } 11 – 999.4 } 10

Re Assay

109 – 900.3 } 6 – 900.2 } 6
10 – 903.3 } 6 – 902 } 6
14 – 900.4 } 6 – 900.3 } 6
15 – 900. } 6 – 900.2 } 6
16 – 900.2 } 6 – 900. } 6

October 5th 1867.

F. G. Bar.

997.6
120 – 998 } 9 – 999. } 10

Toughened bars –

25 – 996. } 9 – 995.8 }
26 – 995.6 } 9 – 995.5 }

October 9th 1867

Ingots

117 – 900.2 – 900.
18 – 900.0 – 900
19 – 900.1 – 900.2
20 – 900.2 – 900.3

F. G. Bar

122 – 998.5 – 999.2
Ingot.
121 – 899.1 – 899.4
22 – 900.1 – 900.0
23 – 900.1 – 900.1

October 10th 1867

Ingots.

124 – 900.8 – 900.5
25 – 901.1 – 900.7
26 – 901.2 – 901.
27 – 901.3 – 901.1
28 – 900.8 – 900.6
29 – 901.3 – 900.8

October 11th 1867.

F. G. Bars.

123 – 998.8 – 998.4
4 – 998.7 – 998.6

Ingots.

124 – 900.8 – 900.6
5 – 901.2 – 900.8
6 – 901.1 – 901.
7 – 901.3 – 901.1
8 – 900.7 – 900.6
9 – 901.3 – 900.8

October 12th 1867

F. G. Bar

125 – 998.4 – 999.

October 13th 1867

F. G. Bar

126 – 998.6 – 998.5
127 – 998.7 – 998.4
128 – 998.4 – 998.4

October 17th 1867

F. G. Bar

129 -998.5 } 9 -998.6 } 10

October 18th 1867.

Ingots

130 -899.9 } -900 } 6
1 -899.9 } -900. } 7
2 -899.9 } -900.2 }
3 -900.2 -900

134 -900.3 } -900.2 } 5
5 -900.2 -900.2
6 -900.2 } 6 -899.8 }
7 -900.1 -900

F. G. Bar

130 -998.7 } 9 -999.1 } 12

Toughened Bars

27 -993.5 } -993.3 } 12
28 -993.6 } 9 -993.7 }

October 23rd 1867.

F. G. Bars

131 -998.6 } -998.3 } 6
132 -998.5 } 7 -998.2 }

Ingots.

138 -900 } -900. } 2
139 -899.9 } 4 -899.3 }
140 -899.8 } -899.8 }
141 -899.9 -899.8

October 24th 1867.

142 -900.1 } -899.8 } 5
143 -899.9 } 5 -899.8 }
144 -900.1 -899.8

F. G. Bar

133 -998.4 } 6 -998.2 } 6

October 25th 1867.

F. G. Bar

134 -998.5 } 7 -998.4 } 7

October 30th 1867.
F. G. Bars.

135 – – 998.8
6 – 998.5 – 998.7
7 – 998.4 – 998.7

November 1st 1867
Toughened Bars

29 – 998.8 – 992.4
30 – 992.6 – 992.4

November 2nd 1867
Ingots

145 – 900.3 – 900.4
6 – 900.4 – 900.5
7 – 900.3 – 900.4
8 – 900.5 – 900.5
9 – 900.4 – 900.5
150 – 900.4 – 900.4

November 4th 1867.
F. G. Bars

138 – 998.4 – 998.5

November 6th 1867
F. G. Bar

139 – 998.4 – 998.4

November 9th 1867
F. G. Bar

140 – 998.41 – 998.4

November 12th 1867
F. G. Ingot

No. 3 – 998.4 – 998.

November 13th 1867
F. G. Bars

No. 141/2 – 998.3 – 999

November 14th 1867.
F. G. Bars

143 – 998. } 4 – 998.3 } 5
144 – 998.2 } – 998.

November 15th 1867
Toughened Bars

131 = 993.3 } 5 – 993.3 } 5
2 = 993.4 } – 993.4

November 18th 1867
Ingots

151 – 900.1 } 5 – 899.9 } 7
2 – 900.2 } – 900
3 – 899.9 } 6 – 900
4 – 900.3 } – 900
5 – 899.9 – 899.9

November 19th 1867
F. G. Bar

145 } – 998. } 5 – 998.2 } 5
146 }

November 23rd 1867
Ingots.

156 – 900.8 } – 900.5 } 9
157 – 900.7 } – 900.8
158 – 898.2 } – 898.1
159 – 899.9 } – 899.6
160 – 900.2 – 900

156 – 900.5 } – 900.5 } 5
7 – 900.4 } – 900.5
8 – 897.9 } 6 – 897.9 }
9 – 899.7 } – 900
60 – 899.8 } – 899.2

November 25th 1867.
Fine Gold Ingot formed

1 – 998.2 } 6 – 998. } 5

November 26th.

Ingots.

161 - 902 } 902
2 - 898.2 } 4 898
3 - 898.9 } 898.9

November 28th 1867

Ingots.

164 - 900.4 } 900.5
5 - 900.5 } 7 900.6 } 8
6 - 900.2 } 900.3

F. G. Bar

147 - 998.3 } 7 998.3 } 9

November 29th 1865

Toughened Bar

X33 - 994.2 } 8 994.3 } 7
134 - 994. } 994.

Tuesday December 3

Ingots

167 - 900.4 } - 900.
168 - 899.7 } 5 - 899.5 } 5
169 - 900.1 } - 900
170 - 899.8 - 900

Fine bar

148 - 9) - 997.6 } 7

Dec 4th

Fine bars

148 - 998.2 } 6 - 998.3 } 5
9 - 998.3 } - 998.2

Thursday Decr. 5th

F. G. Bar

150 - 998.3 } 5 - 998.1 }

Wednesday Dec. 11th

Ingots.

171 - 900.1 | 900.1

2 - 900.4 | 900.2
3 - 900.3 | 7 900.2 | 7
4 - 900.2 | 900.3

December 12th 1867
F. G. Bar
151 - 998.9 | 12 - 999 | 12

December 18th 1867
Gold Ingots
175 - 900.3 | - 900.2
6 - 901.2 (900.6) | - 900.3
7 - 900.3 | 8 - 900.
8 - 900.4 | - 900
9 - 900.5 | - 900.2 | 9

December 16th 1867
Ingots.
180 - 900.2 | - 900.2 | 4
181 - 900.2 | 7 - 900. |

December 19th 1867.
Ingots.
182 - 900.8 | - 900.6
183 - 900.6 | 8 - 900.7
184 - 900.4 | - 900.2 | 8
185 - 900.2 | - 900.4
F. G. Bar.
152 - 998.3 | 8 - 998.4 | 9 -

December 28th 1867
Ingots.
186 - 900.4 | - 900.6
7 - 900.5 | 10 - 900.6 | 4
8 - 900.5 | - 900.7
F.G. Bar
153 - 998.5 | 8 - 998.7 | 11

186 - 900.3 | - 900.2
7 - 900.2 | 7 - 900.1 | 7
8 - 899.8 | - 900.2

December 26th 1867
F. G. Bar
154 - 998.) 5 - 998.) 1

January 2nd 1868
F. G. Bar
1 - 998.) - 997.8) 4

December 28th 1867
Toughened Bars
35 - 993.1 } - 993. }
36 - 992.8 } 11 - 993.1 } 9

January 3rd 1868
F. G. Bar
2 - 998.) 4 - 998) 4

December 30th 1867
F. G. Bar
155 - 998.3) 5 - 998.1) 6

January 6th 1868
F. G. Bar
3 - 998.) 4 - 998.2) 8

December 31st 1867
Ingots.
189 - 900.4 } - 900 }
190 - 900. } 8 - 900 } 8
191 - 900 } - 900 }
F. G Bar
156 - 998.3) 7 - 998.2) 7

January 7th 1868
Ingots.
1 - 900. } - 899.7 }
2 - 899.8 } 6 - 899.6 } 5
3 - 899.8 } - 899.8 }

January 8th 1868
F. G. Bars
4 - 998.) 5 - 997.8) 3

January 11th 1868
F. G. Bars.
5 - 998.3 } - 998.2 }
6 - 998.3 } 7 - 998.2 }
7 - 998.2 } - 998.2 }

January 15th 1868
F. G. Bars
998. 2.17 998. 6
8 - 998 } - 998 }
9 - 998.3 } 5 - 998.2 } 6

January 18th 1868
Ingots.
4 - 900 } - 900. }
5 - 900.1 } 8 - 900.3 } 6

January 20
F. G. Bar
10 - 998.5) 8 - 998.4) 9

January 21
F. G. Bar
11 - 998.3) 5 - 998.2)

January 22
F. G. Bar
12 - broken) - 997.8) 4

January 23
F. G. Bar
13 - 998.3) 5 - 998.2) 7

January 27th
F. G. Bar
14 - 998.) 4 - 997.86) 4
15 - 998.1) 5 - 998.2)

January 30th
F. G. Bar
16 - 998.2 / 5 998.1 / 4

February 1st 1868

F. G. Bar

17 – 992.1)5 – 998.)1

February 8th 1868

F. G. Bar

20 – 995)0 – 995)0

Monday Feby 3rd

Fine G. Ingot.

1 – 995.7)5 – 995.5)2

Fine Bar

18 – 998.4)5 – 998.2)

Toughened bars

1 – 992.3 } – 993.2 }
2 – 991.7 } – 992.5 }

1 – 992.5 } 7 992.3
2 – 991.5 } 991.6

Thursday Feby 6th

F. G. Bar

19 – 995.5)4 – 995.5)5

February 10th 1868

Ingots

6 – 899.4 } – 899.5 }
7 – 900.1 } 4 – 900.4 } 3

February 13th 1868

F. G. Bar

21 – 995.7 } – 996 }
22 – 995.8 } 7 – 996 } 8

Ingots heavy

6 – 899.5 } – 900.2 }
7 – 900.3 } 6 – 900 } 7

Toughened bars

No. 3 – 990.9)7 – 990.8)7

February 17th 1868

Ingots.

8 – 899.6 } – 899.8
9 – 899.5 } 4 – 899.6 } 3
10 – 899.5 } – 899.5 }

February 18th 1868

Ingots.

11 – 899.7) – 900) 4

February 19th 1868

F. G. Bars

23 – 995.8 } – 995.5 }
24 – 995.8 } 6 – 995.5 } 6

February 24th 1868

F. G. Ingots.

2 – 997.1) 4 – 997.2) 1

February 26th 1868

Tongued Bars.

25 – 997.1) – 997) }
26 – 997.2 } 5 – 997 } 3

Ingots.

12 – 898.2 } – 898.2 }
13 – 899.9 } 5 – 900 } 5
14 – 899.6 } – 899.7 }

February 28th 1868

Ingot.

15 – 899.3) 2 – 899.) 2

March 4th 1868

Stand Tongued bars

14 – 902.7) 3 – 903.1) 8

March 5th 1868
Ingots.

16 - 900.3 } - 900.2 }
17 - 900.1 } 7 - 900 } 7
18 - 900 } - 900 }

March 10th 1868
F. G. Bar

27 - 997.8 } 3

March 11th 1868
F. G. Bar

28 - 997.1 } 3 - 996.8 }

March 12th 1868
Gold Sample.
No - 987.5

March 14th 1868
Toughened Bar

5 - 993.2 } 4 - 993.5 } 3

March 16th 1868
Ingots.

19 - 900.1 } - 900.2
20 - 899.8 } 3 - 900.2 } 5
21 - 900 } - 900.2

March 17th 1868
F. G. Bar

29 - 997.2 } 4 - 997.4 } 4

March 18th 1868
F. G. Bar

30 - 899.4 } 6 30 - 997.1 } 5

Thursday March 19th 1868
F. G. Bar
31 – 997.) 3 – 997.) 2

March 24th 1868
Ingots
22 – 899.7 } – 899.7 }
23 – 899.7 } 3 – 899.7 } 3
F. G. Bar
32 – 997.) 5 – Dd.)

March 25th 1868
F. G. Bar
33 – 997.3) – 997.4) 7

March 28th 1868
F. G. Bars
34 – 997.4 } 7 – 997.3 }
35 – 997.4 } – 997.1 }

March 28th 1868
Fine bar slips melted
– 986.1) 5 – 986.7
Ingot slips
– 898.) – 898.3) 5

March 31st 1868.
Fine G. bar
36 – 997.4) – 997.4) 7
Ingot Slip.
– 899.6) 1

April 2nd 1868
F. G. Bars.
37 – 997.2) 38 – 997.2) 3

April 3rd 1868
Toughened bars
6 – 995.9) 9 – 996. }
7 – 995.8 } – 995.9 } 7

April 6th 1868

Ingots

26 - 899.
25 - 899.6 } 2 - 899.7 / - 899.5 } 2

April 7th 1868

Toughened Bars.

8 - 903.
9 - 902.3
10 - 906.

8 - 903.1
9 - 902.4
10 - 906.1

Medal Ingot

2 - 997.5 grains / 988.3 } 2 - 997.5

April 8th 1868

Ingots

26 - 900.2
27 - 899.8 } 6 - 900.3 / - 899.8 } 6

Fine Bar

39 - 995.5) - 995.7) 6

April 9th 1868

F. G. bar

40 / 41 - 997.3) 7 - 997.2) 5

April 11th 1868

Toughened bars

11 - 990.4
12 - 990.4 } 7 - 990.6 / - 990.6 } 8

April 15th 1868

Fine G. Bar.

42 - 997.1 - 997.) 2

April 16th 1868

F. G. Bar

43 / 44 / 45 - 997.3) 6 997.5

April 17th 1868

Ingots.

28 – 900.5 – 900.4
29 – 900,5 – 900.5
30 – 900.6 9 – 900 4 9
31 – 900.3 – 900 3
F. G. bar.

46 – 997.8 – 997.9
47 – 997.8 10 – 997.4

April 22nd 1868
F. G. Bars.

48
49 – 997.4 – 997.2
50

51 – 997.4 – 997.2

April 25th 1868
F. G. Bar

52 – 997.3 – 997.2

April 28th 1868
Medal Ingot.
– 997.4 – 997.3 6
F. G. Bar
№ 53 – 997.4 – 997.3

April 30th 1868
F. G. bars
54-55 – 997.2 – 997.1 5

~~April~~ May 1st 1868
F. G. bar
56 – 997. – 997 4

May 6th
F. G. Bar
57
58 997.3 P.B 997.4

May 9th 1868.
Fine Gold Bar.
59 - 997.3 | 6 - 997.3)

34 - 900.4 | - 900.5 | 9
35 - 900.7 | - 900.7 |
36 - 900.2 | - 900.2 |

May 14th 1868
Fine Gold Bar
60 - 997.3 | 5 - 997.3)

May 21st 1868
Fine Gold Bar.
62 - 997.1 | 5 - 997.3)

May 15th 1868
Fine Gold Bar
61 - 997.1 | 4 - 997.)

May 27th 1868
F. G. Bar.
63 - 997. | 3 - 996.6)

May 18th 1868
Tonyhead Bar
13 - 990.7 | 990.6 | P.6

May 28th 1868
F. G. Bar
64 - 997.5 | 7 - 997.6)

May 20th 1868
Ingots.
32 - 900.2 | - 900.2 |
33 - 900.3 | - 900.2 |

May 30th 1868
F. G. Ingot
3 - 996.2 | 5 - 996.8 | 6

June 3rd 1868
Base bar
No. 15 – 537 G / 4335

June 5th 1868
Fine Gold Bar
65 996.8 | 2 997.3

June 11th 1868
F. G. Bar
66 – 997.2) 6 – 997.)

June 17th 1868
F. G. Bar
67 – 995.8 } 4 – 995.8 } 1
68 – 997.3 } 996.7 }

June 18th 1868
F. G. Bar
69 – 995.8) 4 – 995.8) 2

June 25th 1868
F. G. Bar
70 – 995.6) 2 – 995.7) 2

June 27th 1868
Ingots
37 – 899.7 } 5 – 899.8 } 3
38 – 899.8 } 5 – 899.7 } 3

July 2nd 1868
F. G. Bar
71 – 995.7) 2 – 995.6) 2

July 3rd 1868
F. G. Bar
72 – 996) 4 – 996.) 4

July 7th 1868
F. G. Bar
73 – 996) 4 – 996.1) 2

July 10th 1868
F. G. Bar
74 - 996. } 3 - 996 }

July 11th 1868
F. G. Bar
75 - 996.1 } 5 996.2

July 16th 1868
F. G. Bar
76 - 996.2 } 3 - 995.8 }

July 17th 1868
F. G. Bar
77 - 995.8 } 3 996.

July 18th 1868
F. G. Bars.
78 - 995.9 } 996.2 }
79 - 996.0 } 996.2 } 7

Toughened bars.
16 - 990.9 } 5 - 991.3 }
17 - 991.2 } - 991.2 } 7

July 21st, 1868
Ingots.
29 - 899.5 } 3 - 899.8 }
40 - 899.5 } - 899.6 } 4

July 21st 1868
F. G. Ingot
Toughened bar 4
1 - 4 - 997.4 } 9 - 997 } 9
18 - 992.3 } - 992.1 }
19 - 992. } - 992. }

July 28th 1868
Ingots.
41 - 899.3 } - 899.9 }
42 - 899.5 } - 899.6 }

July 29th 1868
F. G. Bar

80 – 996.1 } 5 – 996 |

August 5th 1868
F. G. Bar

83 – 995 } 3 – 996.1 } 4

July 30th 1868
F. G. Bars

81 – 996.1 } 6 – 996.1 } 7
82 – 996.2 } – 996.1 }

August 6th 1868
F. G. Bar

84 } – } 5 –
85 – } 996.3 } – |

July 31st 1868
Ingots

43 – 900.3 } – 900.4 }
44 – 900. } 7 – 900.3 } 9
45 – 900.3 } – 900. }

45 – 899.7 } 5 – 899.9 } 4
45 – 899.7 }

August 10th 1868
86 – 996.3 995.0

August 4th 1868
Ingot

46 – 899.7 } 3 – 899.7 } 3

Aug 12th 1868
Ingots.

47 900.2 } 8 899.7 } 5.
48 900. } 899.7 }

Aug 15

87 } 996.5 | 997. 5
88 }

Aug 20th 1868
Fine Gold Bars

89, 90 } 997.3 | 13 | 996.3 | 9
91 997.5 | | 996.5 |

Aug 20
Longhurst Bars

20 993.3 | 13 | 992.8 | 9
20 993.4 | | 992.9 |

Aug. 22nd 1868
F. G. Bar

92 – 996.1)4 – 996.7

August 24th 1868
F. G. Bar

93 – 996.2)5 –

August 26th
F. G. bars.

94, 95, 96 – 996. | 3 | 9 | 3

August 31st 1868
F. G. Bar.

97 – 996.2)5 – 996.4)

September 3rd
F. G. Bar

98 – 996.)3 – 996.5

September 3rd
F. G. Bar

99 – 996.4)5 – 996.5)

September 5th
F. G. Bar
100 – 996.5)8 – 996.5)8

September 8th
F. G. Bar
101 }
102 } – 996.8)5 – 996.7)

September 10th
F. G. Bar
103 – 996.2)5 – 996.4)

September 16th
F. G. Bar
104 – 996.1)3 – 996.5)

September 17th
Fine G. Bars
105 }
6 } 996.4 } – 997 }9
7 }

108 – 996.4) – 996.8)7
Ingots
52 – 899.7) – 899.9)5
53 – 899.7)4 – 899.9)

September 21st
Fine G. Bar
109 – 995.6)2 – 996.8)

September 24th
Fine G. Bar
110 }
111 } – 996.3 }5 – 996.8 }5
112 }

September 28th
Toughened Bars
22 } – 993.3 } 993.4)
23 } – 993.1 }5 – 993.3)

Septr. 30th 1868

Ingots.

54 – 899.7 } – 900.1
5 – 899.7 } – 899.9
6 – 899. } – 900.

F. G. bar

113 } – 99 7 } 5 – 996.9 5
114 }

56 – 899. } 2 – 899.5 0

118 – 996.5 } 4 – 996.6 } 6

Ingots.

57 – 899.6 } 57 – 899.7 }
58 – 899.5 } 3 58 – 899.7 } 4

October 3rd 1868

Fine Gold Ingots

No. 6 – 996.8 } 5 – 996.9 }

Toughened bars

24 – 985.2 } 5 – 985.1 }

October 5

Ingot

59 899.52 } 59 899.52

~~September~~

October 1st 1868

F. G. Bars

115 – 996.6 } – 996.6
6 – 996.0 } 5 – 996.6 } 6
7 – 996.7 } – 996.6

October 8th 1868

F. G. Bars

119 } – 996.9 } 7 – 996.8 } 6
120 }
121 – 996.9 } – 997

October 2nd 1868

F. G. Bar

October 15th 1868
F. G. Bars.

122 - 996.3)2 - 996.5)3
123

October 22nd 1868
F. G. Bars.

127 } - 996.4)3 996.3)
128 }

October 19th 1868
F. G. Bar

124 - 996.4)3 - 996.4)3

October 21st 1868
F. G. Bar

126 - 996.9)8 - 997

October 19th 1868
Ingots.

60 - 900)5 - 900.2 {7
61 - 899.9) - 900. (

F. G. Bar

125 - 996.9)8 997.)8

October 29th 1868
F. G. Bar.

130 } - 996.2)2 6.1)
131 }

October
November 2nd
Toughened Bars

25 - 993.1)6 - 993.4)8
26 - 992.8 (- 993 (

November 4th 1868
F. G. Bar
132 - 996.2 | 996.3 |

November 6th 1868
Ingots.
62 - 99.3 } - 899.4
63 - 99.2 } - 899.8
64 - 899.7 } 7 - 899.9 } 7
65 - 99.7 } - 899.8 }
F. G. Bars
133/4 } - 996. } 7 - 9968 }
135 - 996.9 } - 997.1 } 8

November 7th 1868
Ingots
66 - 900.2 } - 900.2
67 - 900.1 } 7 = 900.2 } 7
68 - 900. } - 900
69 - 899.8 } - 899.8

F. G. Bar
136 - 996.9 | 8 - 996.9 - |

Novembe 9th 1868
Ingots.
70 - 899.9 | 3 - 900. } 8

November 12th 1868
F. G. Bar
137 | - 996.4 | 996.7 |

November 13th 1868
F. G. Bars.
138 - 996.4 } 3 - 996.5 }
139 - 996.3 } - 996.4 }

November 14th 1868
F. G. Bar
140 - 996.7 } 6 997. } 9
Toughened bar } —
3.0 —
2.8 —

27 - 992.6 } 6 - 992.8 } 9
28 - 992.5 } - 992.8 }

November 16th 1868
F. G. Bar
141 - 996.4) 4 - 996.5)

November 17th 1868
Ingots.
71 - 899.3 } 3 - 899.4 } 3
72 - 899.5 } - 899.4 }

November 18th 1868
Ingots.
73 - 899.1 } 5 - 900.2 } 7
74 - 899.9 } - 900.2 }

142 }
143 } - 996.9) 7 996.4
144 }

November 23rd 1868
F. G. Bar
145 - 996.2) 3 996.5)

November 26th 1868.
F. G. Bar
146 } - 996.4) 3 996.3)
4

November 28th 1868
F. G Bars
148 - 997.1 } 2 - 997.1 }
149 - 997. } - 997 }

December 2nd
F. G. Bar
150 - 996.4) 3 - 996.)

December 4th —
F. G. Bars
151 } - 996.3) 3 996.4
2 }

December 7th 1868
Ingots

75 - 900.1 } 6 - 899.8 }
76 - 900.2 } - 900 } 5

December 8th 1868
F. G. Bar

153 - 996.4) - 996.7)

December 9th
F. G. Bar

154 - 996.4) 4 - 996.6)

December 14th 1868
Toughened bars

29 - 992.5 } 10 - 992.7 }
30 - 992.7 } - 993. } 8
31 - 905.3 } 8 - 900.2 } 1

29 - 992.4 } 7 - 992.3 }
30 - 992.5 } - 992.4 } 8
31 - 905.3 } 7 - 905.1 } 5
156 - 996.8) 7 - 996.8) 8

December 16th 1868
Ingots

77 - 900.2 } - 899.9 }
78 - 900.3 } - 899.8 }
79 - 900. } 7 - 899.9 } 5
80 - 900.3 } - 900 }

December 17th 1868
F. G. Bars

157 } 8 - 996.4 (4 996.4)

December 19th 1868
F. G. Bar

159 - 996.8) 5 -

December 23rd 1868
Ingots.

81 – 900.3 } – 900.2 } 5
82 – 900.0 } – 899.8 } 4

December 30th 1868.
F. G. Bars

160 – 996.8 } – 996.6 }
161 – 997 } – 997.2 } 8
162 – 997 – 997.2 }

January 2nd 1869
F. G. Bars

163 – 996.6 } – 996.6 }
164 – 996.5 } – 996.6 }

January 2nd 1869
Ingots

1 – 900.2 } 7 – 899.8 } 5
2 – 900.1 – 899.8 }

January 7th 1869
F. G. Bars

1 } – 996.2 | 2 996.2
2 }

January 8th 1869.
F. G. Bar

3 – 996.3 | 2 – 996.4 |

January 12th 1869
F. G. Bar.

4 } – 997.2 | 12 – 997.4 |
5 }
6 } – 997.3 | 12 – 997.4 |
7 }
8 – 997.3 | 12 – 997.2 | 8
9 – 997.3 | 12 – 997.3 |
10 } – 997.2 | 12 – 997.4 |
11 }

January 15th 1869
F. G. Bar

12 – 996.5 | 3 – |

January 16th 1869
F. G. Bar
13 – 996.4 – 996.6 5

January 18th 1869
F. G. Bar
14 – 996.6 5 – 996.3

January 20th 1869
Toughened Bars
1 – 974.3 } 9 974.6 }
2 – 970.4 } 9 970.2 } 9

January 20th 1869
Ingots
3 – 900.2 } 7 – 900 }
4 – 900.2 } 7 – 900.2 } 7
Fine bar
15 – 996.6 5 – 996.6

January 21st 1869
F. G. Bar
16 – 996.3 3 996.5

January 22nd 1869
F. G. Bar
17 – 995. 0 } 995 }
(17) – 995.3 5 } 995.2 } 3

January 27th 1869
F. G. Bars
18 – 995. } 2 – 995.1 }
19 – 995.1 } – 995.2 }

January 28th 1869
F. G. Bar
20 – 995.4 } 2 – 995 }
21

February 3rd 1869
F. G. Bars

22, 23, 24 — 995.2 | 5 | 995.2

February 4th 1869
F. G. Bars

25 — 994.6 | D | 994.4

February 10th 1869
Ingots. T. bar & F.G.

5 — 900.1 — 899.9
6 — 900.4 — 900.3 | 7
7 — 900.2 — 900. | 7
FB 3 — 895.5 — 895.4

26 — 995.4 | 8 | 995.5

February 11th 1869
F. G. Bars

27, 8 — 995.5 —
9 — 995.5 | —
30 — 995.5 | —

February 13th 1869
Toughened Bars

4 — 996.5 | 3 | 996.4 | 0

February 16th 1869
Fine bars

31 — 995.9 | 996.1
32 — 996.1 | 996.2 | 0
FG Ingot 993.6 | 993.6

Tough bars

5 — 974.7 | 974.7 | 0
6 — 975.7 | 9 | 976
7 — 972.5 | 8 | 972.6 | 7

February 17th 1869

Ingots

8 – 899.7 } – 899.3
9 – 900.1 } 5 – 899.7 } 5
10 – 900.2 } – 900 } 5
11 – 900.5 } – 899.9 }

9 – 899.7 } – 899.9
11 – 900.3 } 3 – 899.6 } 2

February 20th 1869

Tough bar, Stans

8 – 903.2 } – 904.7
9 – 903.1 } 9 – 902.9 } 9
10 – 903.2 – 903.3

F. G. bar

33 } – 996. } 9 996.1 } 11
34 }
35 – 995.5 } 5 – 995.8 } 8
TB. 11 – 869.5 } 6 – 869.4 } 6

February 23rd 1869

Ingot

12 – 900.4 } – 900.2
13 – 900.3 } 8 – 900 } 7
14 – 900.3 – 900

February 25th 1869

F. G. Bars

36 } – 995.5 – } 3 995.7 } 7
7 }

March 1st 1869

Fine Bar

38. – 995.2 } 3 – 995.4 } 3

March 3rd 1869

Fine bar

39 – 995.4 } – 995.6 }
40 – 995.4 } 5 – 995.7 } 5

March 5th 1869

41 - 994.8
42 - 995.6 | 5 | 994.8 / 995.7 | 7

March 8th 1869

Ingots.

15 - 900.4
16 - 900.3
17 - 900.3
18 - 900.3 | 7 | 900.2 / 900.1 / 900.2 / 900.2 | 6
19 - 899.4 | 2 | 899.2 | 0

March 10th 1869

F. G. Bar

44 - 993.2
55 | 5 | 993.2 | 6

March 13th 1869

Stand Roughed & Fine bars

12 - 916.3 } 9 | 916.3 | 10
13 - 921.7 } | 921.5 |
Fine

46 - 993.5 } 8 | 993.7 |
7 - 993.5 } | 993.6 | 8
8 - 993.6 } | 993.6 |

March 16th 1869

Ingots

20 - 900.7 } 9 | 900 / 899.9 / 851.5 | 0
1 - 900.3 } | 899.7
2 - 900.3 }
3 - 900.
Slit - 949.1 | 948.7 |

20 - 900.2 } 6 | 900.1 / 899.9 / 899.9 / 899.9 / 948.5 | 6
1 - 899.9 }
2 - 900 }
3 - 899.8 }
Slit - 948.4 }

March 17th 1869

F. G. Bars

49 } -993.1 | -993.2 |
50 } | | 2
Ingot 2 -987.7 | -987.6 |
T.B. 15 -988. | -987.8 |

March 18th 1869

F. G. Bar

51 -996.4) 4 -996.8)

March 19th 1869

52 -996.7 | -996.8 | 5
53 -996.7 | -996.9 | 5

March 23rd 1869

F. G. Bar

54 -997.5) 7 -997.9) 6

March 24th 1869

F. G. Bar
RA.

54 -997.7) 7 -997.7) 7

Ingot.

24 -900.4) -900.3) 7
25 -900.3) 7 -900.2)

M&R.

1 -899.5 - 899.5

March 25th 1869

F G Ba

55 } -997.1) 5 997.1) 5
56 }

March 26th 1869

F. G. Ingot.

No. 3 -997.) 6 -997.2) 8

March 27th 1869

Sample

993.8 | P/. 2

March 31st 1869
F. G. bars
57 } 996.7 } 2 996.8 } 2
58 }

April 2nd 1869
F. G. Ingot, bar &c
4 - 997.4 } 996.4 }
60 - 997.3 } 7 997.3 } 9
Grain 3 - 972.2 } 972.3 }
4 - 997. } 4 996.8 } 4

April 5th 1869
F. G. Bars
61 - 995.6 } 4 995.7
62 - 996.8 } 3 996.8

April 7th 1869
F. G. Bars
63 - 997. } 6 997.2
64 } 997.2 } 6 997.1
65 }

April 8th 1869
F. G. Bar
68 - 997 } 4 996.9

April 9th 1869
F. G. Bar
69 - 996.9 } 4 997

April 10th 1869
F. G. Bar
70 - 997.1 } 4 997.

April 14th 1869
F. G. Bar
71 - 997.4 } 7 997.3 } 7
72 997.1 } 5 997.2 }

April 15th
73 } 997.2 } 4
74 } 997.1 }

Saturday April 17th
F. G. Bar

95 - 997.1 | 4 - 997.3

April 20th 1869
F. G. Bar

76 - 996.9 | 4 - 997 |

April 21st 1869
F. G. Bar

77 - 997.2 | 6 - 997.3 |
78 | 7
79 | - 997.1 | - 997.3 |

April 23rd - 1869
F. G. Bar

80 - 996.9 |

TB - 16 - 926.8 - 926.5

April 28th 1869
Ingots.

26 - 900.9 | 10 - 900.7 |
27 - 900.9 | - 900.3 |
28 - 900.7 | - 900.5 |
29 - 900.5 | - 900.2 |

26 - 900.5 | 8 - 900.3 |
27 - 900.5 | 900.3 |
28 - 900.3 | 900.1 |
29 - 900.2 | 900. |

April 29th

30 - 900.4 | 8 - 900.2 |
31 - 900.2 | 900 1 |
32 - 900.5 | - 900.4 |

Fine bars

81 - 998. | 10 - 997.2 |
82 | - 998. |
83 | - 997.8 |
84 - 997.7 | - 997.1 |
85 - 997.6 | - 997.3 |

May 5th 1869.

F. G. Bars

86 } - 997.3 | 7 - 997.6 | 10
87 }

F.G. for M.C. - [illegible] | [illegible]

May 7th 1869

Toughened Bar

17 - 919.11 | - 919.2 |

May 10th 1869

Ingots.

33 - 900.3 } - 900 } 2
34 - 900.2 } 5 - 899.7 }
35 - 900.1 } - 899.7 }
36 - 900.1 } - 899.7 }

May 11th 1864

F. G. Bars

88 - 997.8 | 9 | 997.9 | 10

N. York Bar

19 - 998 - 997.6
20 - 998. - 997.6
21 - 997.5 - 997.

May 13th 1869

Ingots.

37 - 900.5 } - 899.7 } 8
38 - 900.4 } 8 - 900.3 }
39 - 900.4 } - 900.2 }
40 - 900.3 } -

F.G. Bars

89 } - 997.6 | 9 - 998 | 12
90 }
91 - 997.7 | - 998 |

T.B.

18 - 903 | - 902.9 | 10
19 - 902.7 | 9 - 902.7 |

May 15th 1869
Ingots.

40 – 900 } – 899.8 }
1 – 900.2 } 6 – 900.2 } 6
2 – 900. } – 899.9 }

May 17th 1869
F. G. Bar

92 – 996.9 } 2 – 997.2 }

May 20th 1869

20 – 989.8 } – 989.7 }
21 – 989.5 } 7 – 989.2 } 7

May 20th 1869
F. G. Bars

93 } – 997.3 } 5 997.2 }
94 }

Friday May 21st
Ingots.

43 – 900. } – 899.7 }
4 – 899.9 } 4 – 899.7 } 3
5 – 899.5 } – 899.4 }

46 – 900 } – 900 }
7 – 900.1 } 5 – 899.8 } 6
8 – 900.1 } – 899.8 }

MXR Sample – 967.4

May 26th 1869
F. G. Bars

95 – 997.2 } – 997.5 }
96 – 997.1 } 6 – 997.4 } 2

May 27th 1869
Ingots.

49 – 900.3 } – 900.4 }
50 – 900.5 } – 900.6 }

51 – 900.5 – 900.4
52 – 897.3 – 897.8 (10)
53 – 900.3 – 900.5 (9)
54 – 902.5 – 902.9

F. G. Bars

97 – 997.3 (7) 997.7
100 – 997.4 997.5 (10)

May 28th 1869
Ingots

55 – 900.3 – 900.3
6 – 900.4 – 900.3 (10)
7 – 900.3 – 900.2 (8)
8 – 900.3 – 900.2

59 – 899.5 – 899.6
60 – 899.5 – 899.7 (3) (4)

May 31st 1869
Toughened bar

22 – 993.8 (3) 993.7 (3)

June 3rd 1869
F. G. Bar

101 – 997.6 (8) 997.6

June 3rd 1869
Ingots.

61 – 900.3 – 900.4
2 – 900.3 – 900.7
3 – 900.3 – 900.4 (12)
4 – 900.1 – 900.4
5 – 900.1 – 900.4

Steel Tough Bars

23 – 903.8 – 903.6
4 – 904.0 (8) – 903.7 (8)
5 – 903.8 – 903.5

Fine bar

102 – 997.3 (7) 997.5

Re Assays over

61 – 900.3 } – 900.2
2 – 900.4 } – 900.2
3 – 900.3 } 10 – 900.2
4 – 900.3 } – 900.1
5 – 900.2 } – 900.1

June 7th 1869

66 – 899.8 } – 899.8
7 – 900.6 } – 900.6
8 – 899.9 } 3 – 899.9
9 – 900.5 } – 900.5

F. G. Bar

103 – 997.3 } 1 – 997

Ingots

70 – 899.2 } – 899.5
1 – 902.3 } 2 – 902.2
2 – 899.1 } – 899

June 9th 1869

Ingots

73 – 900.6 } – 900.7
4 – 900.6 } – 900.7
5 – 900.5 } – 900.3
6 – 900.7 } – 900.6

June 9th 1869

F. G. Bars

104 }
105 } – 997. } 3 997.3 8
106 }

June 10th 1869

Ingots

77 – 908. – 908
8 – 899.9 } 5 – 899.7
9 – 900.9 } – 900.8
80 – 900. } – 900.2

June 11th 1869
F. G. Bar

109 – 997.1 } 5 – 997.3

Ingots

81 – 899.7 } 3 – 899.8 } 5
2 – 899.5 } 3 – 899.8 } 5
3 – 899.7 } – 899.9 }

June 12th 1869
Toughened Bar

36 – 904.2 } 3 – 903.9 } 2

June 14th 1869
Ingots

84 – 898.2 } – 898.3 }
5 – 898.7 } 2 – 898.9 } 6
6 – 902.9 } – 902.9 }

June 16th 1869
Fine G. Bars

110 – 997.2 } 5 – 997.1 }
111 } – 997.1 } – 997.2 } 4
112 }

June 18th 1869
F. G. Bars

113 – 997.2 } 3 – 997.1 } 3
114 – 997.1 } – 997 }

June 19th 1869
F. G. Ingot

No 5 – 996.6 } 5 – 996.7 } 4

June 22nd 1869
900.6 } 6

87 – 900.3 } – 900.3 }
8 – 900.5 } – 900.7 }
9 – 900.5 } 8 – 900.3 } 7
90 – 900.3 } – 900.3 }

June 23rd 1869

Ingots

91 - 900 } - 900.1
2 - 899.9 } - 899.9 } 5
3 - 900 } - 900.1 }
4 - 899.9 } - 899.9 } 5

F. G. Bar

118 - } 997. } 4 997.
116 - }

June 25th 1869

F. G. Bar

117 - 996.9 } 3

June 26th 1869

F. G. Bars

118 } - 997.3 } 6
119 }

June 28th 1869

F. G. Bar 4

120 - 997. } -

July 1st 1869

Ingots

95 - 900.3 } - 900 }
6 - 900.3 } 8 - 900.2 } 7
7 - 900.2 } - 900. }

F. G. Bars

121
2 - 997.4 } 8 - 997.6 } 11
123 - 997.3 } - 997.7 }

July 2nd 1869

Ingots.

98 - 899.9 } 4 - 899.8 }
99 - 899.8 } - 899.5 } 5
F. G. Bar 899.8 . 4

124 - 997 } - 997.3 5

July 6th 1869
F. G. Bars
125 – 996.9 } 3 – 997.2

July 8th 1869
F. G. Bar
126 – 997.5 } 5 – 997.3

July 9th 1869
Stand Fought bar
27 – 956.3 } 7 – 956 } 6
28 – 914.8 } 7 – 914.7 }

July 12th 1869
Ingots.
100 – 899.7 } – 900 }
1 – 900.1 } 5 – 900 } 6
2 – 900.3 } – 899.9 }
F. G. Bars

127 – 997.2 } 6 – 997.
128 – 997.2 } 6 – 996.5

July 15th 1869
F. G. Bar
129 } 30 – 997 } – 997.3 }
131 – 997.2 } 5 – 997.3 } 6
132 – 996. } – 997 }

July 17th 1869
F. G. Bar
133 – 997. } 4 – 997.1

July 21st 1869
F. G. Bar
134 – 996¼ } 5 – 996¼

~~July 22nd 1~~

July 22nd 1869
F. G. Bars
135 } - 996.5) 5
136 } - 996.5)

July 24 F.G Bars
137 996.9 }
138 996.8 } 6

July 31st 1869
F G Bar
14 - 996.6) 5 - 996.5) 4

August 4th 1869
Toughend bars
29 - 899.) 5 - 899.) 4
F. G. Bars
143 } - 996.7) 5 - 996.8) 5

August 11th 1869
F. G. Bars
145 } - 996.9) 7 997.) 7
146 }

Aug. 18th 1869
F. G. Bars
147 - 996½ —
8 -
9 - 996½ —

Aug. 19th 1869
150 - 996.8 } - 996.9 } 7
151 } - 996.9 } 997) 7
152 }

Aug 21st 1869
F. G. Bar
153 - 996.4) 4 996.3

Aug 25th 1869
F. G. Bars
154/5 — 996.4 | 3 —

Aug. 26th 1869
F. G. Bar
156 — 996.7 | 5 — 996.8 | 5

Aug. 28th 1869
F. G. Bar
157 — 996.8 | 5 — 997 | 8

Sept 2, 1869
F. G. Bar
158/159 — 996.9 | 8 — 997.1

Sept 3 1869
F. G. Bar
160 — 996.7 | 7 — 996.9

Tuesday Sept 7 1869.
Fine Toughened Bars.
30 — 993.5 | 8 — 993.7 | 8
31 — 993.8 | 993.7 |

Wednesday Sept 8 1869.
Gold Ingots.
103 — 899.9 | 6 — 899.8 |
104 — 900 | 900.1 |
105 — 900.3 | 900.1 |

Friday Sept 10.
Ingots
106 — 900.1 | 5 — 900
7 — 899.8 | 899.6 |
F. G. Bars
161/2 — 996.7 | 5 — 997

Saturday Sep 11
F. G. Bar
163 – 996.7 (4) – 996.6

Monday Sep 13
F. G. Bar
164 – 996.9 (6) – 997.

Tuesday Sep 14
F. G. Bar
165 – 996.8 (5) – 996.9

Wednesday Sep 15
F. G. Bar.
166 (7) – 996.8 (5) 996.8
Toughened bar
32 – 993.6 (5) – 993.5 (5)

Friday Sepb. 17
Ingots.
108 – 900.5 (5) – 900.3
9 – 900.4 (8) – 900.3 (8)
10 – 900.4 (8) – 900.3 (8)
11 – 900.5 (5) – 900.3
F. G. Bar
168 – 996.8 (5) – 997.

Monday Sep 20
Toughened Bar
33 – 994.7 (8) – 995. (8)

Wednesday Sep. 22
F. G. Bars
169 (5) – 996.8 (5) 997
176 (5)

Monday Sept. 27

Tough bar

34 — 994.7) 7 — 994.8

F. Bar

171 — 996.9) 8 996.9

Wednesday Sep. 29

F. G. Bar

172 — 997.) 8 — 997.)

Thursday Sep. 30

Ingots

112 — 911.2) 911.2

3. 901.2) 901.

4 900.1) 9 900.3) 10

5 900.7) 900.7)

F. G. Bars 12

173 3/4 } 997.3 } 997.5 } 10

175 } 997.4 } 997.8 } 10

Monday Oct. 4

F. G. Bar

176 — 997.) 8 997.3

Tuesday Oct. 5

177 — 996.9) 6 — 997) 7

Tough bar 6

35 — 994.8) — 995.2) 7

Wednesday Oct 6

Tough bar

36 — 902.3) 5 — 902.3) 5

178 } — 997) 7 997

Ingots

116 — 900.2 } — 899.9

7 — 900 } 7 — 999.7 } 6

8 — 900.3 — 900

119 — 900.5 } 9 — 899.98

120 — 899 — 899

121 — 900.4) — 900

Thursday Oct 7/69

J.G. Bar 180

996.9 | 996.9 | 6

October 11th 1869

Ingot

122 – 900.5 } – 900.4 } 8

23 – 901.3 } – 901.3 } 8

F.G Bar

181 – 997 | 3 997

October 14th 1869

F. G. Bars

182 – 996.9 } – 996.9 } 6

3 } – 997 } – 997

4 } – 997 } – 997

5 – 997 } – 996.8 }

6 – 997 } – 997 }

7 – 996.9 } – 997 }

October 20th. 1869

F. G. Bars

188 } – 996.7 } 5

189 }

October 23rd 1869

F. G. Bar

190 – 996.2 } – 996.2 }

October 25th 1869

F. G. Bar

996

190 – 996.2 } 6 – 996.4 } 7

Tough bar

37 – 996 } – 996 } 7

October 27th 1869

F. G. Bars

191/2 } – 996.4 } 3 – 996.6 } 5

2

Feb 30th

193
4
5
6
} 996.8 | 996.5 | 5

November 2nd 1869
F. G. Bars

197 – 996.8 }
8 – 996.9 }

November 3rd 1869
Ingots

124 – 900.3 } – 900.6 }
5 – 900. } – 899.9 }

F. Bars.

199 }
200 } – 997. | 997. | 8

126 – 900.2 } – 899.9
1 – 900.3 } – 899.9

8 – 900.2 } – 900.1 | 6
FB 38 – 906.3 } – 906.)

November 5th 1869
F. G. Bars.

201 }
7 } – 996 } 5 – 996.2 } 7
208 } – 996 } – 996.1 }
14 }

November 6th 1869
Tough bar

30 – 994.2 } 5 – 994.4 5

F.G. Bar.

221 }
2 } – 996.2 } 996.2 } 5
3 – 996.7 | 996.8 | 1

November 10th 1869
Iron bars.

224 }
237 } – 996.6 } 8 997. | 6
238 – 997.
39 } – 996.6 } 997.4 | 996.8
40 }

November 11th 1869

F. G. Bars

224, 237 – 996.4

238 – 996.8 } 996.7

239, 240 – 996.2 } 996.2

November 15th 1869

Tough bars

40 – 993.2 (8) 993.5 (8)

41 – 911.4 (5) 911.5 (6)

F. G. Bar

242 – 996.5 (6) – 996.7 (5)

November 16th 1869

F. G. Ingot & Bars

Ingot – 996.7 (6½) 997 (8)

243 – 997 (6½) – 997

244 – 996.8 – 997.1

November 17th

Ingot.

124 – 900.1 – 899.5

30 – 900.2 – 899.9

1 – 899.9 – 899.7

2 – 900.8 – 899.1

3 – 900.2 – 899.9

FG Bars.

262, 263, 264 – 996.8 (5) – 996.7 (5)

FB 42 – 975.9 – 976.1

November 19th 1869

Ingots

131 – 899.8 (0) 900. (3) – 900.1 (3)

November 23rd

Toughened Bars

48 – 994.6 (5) – 995.4

November 24th 1869

Ingots.

135 – 898.8 } – 898 } 9
6 – 900.9 } – 900. } 8
6 – 900.9

137 – 900.5 } – 900.5 } 9
8 – 900.6 } – 900.3 } 8

F Bar

265 } – 997 } 9 997.1 } 8
6 }

267 –)

Nov 26th 1869

Line Ingt.

997.3 | 5 997.5 | 8

Nov. 30th 1869

Ingots.

139 – 899.9 } – 900 }
140 – 900.1 } 8 – 900. } 6
1 – 900. – 899.8 }

Bars

268 996.9 } 8 – 997.3 } 9

F. G. Bars

769 } – 997.2 } 5 997.2 } 3
270 }

December 6th – 1869

F. G. Ingot.

0 – 996.6 } 9 – 996.4 } 6

F. Toughened Bar

44 – 995.4 } 5 – 995)
45 – 896.2 } 2 996.4

December 9th – 1869

F. G Bars.

171/2 } – 997.3 } 5 997.4 } 5
3
Tough bar

46 – 932. } 2 – 931.8 } 3

Dec. 14th – 1869

F. G. Bar

274 – 997.1 } 5 – 997

Decr. 15th 1869.
F. G. Bars

2/5/6 – 997.3 | 6 | 997.15

December 24th
Tough – bars

48 – 992.5 | 4 | 993.

Decr. 18th 1869
Ingots

142 – 900.3 | – 900.2 | 8 | – 900.5
3 – 908.3 | – 908
4 – 900.7 | – 900.5
5 – 900.2 | – 900.1

T Bar.

47 – 995.4 | 8 | 994.9 | 5

December 29th
F. G. Bars

280/1 – 997.4 | – 997.5 | 7 | – 997.5
282 – 997.3 | – 997.5
Slip – 994.7 | – 994.9

December 22nd 1869
F. G. Bars.

277/8/81 – 997.2 | 5 | 997.2

January 5th 1869
Ingots.

1 – 899.3 | – 899.2 | 5 | – 899.7 | 3
2 – 900 | – 899.7
3 – 900 | – 899.8
Slip – 900.71 – 900.4

F.G. Bars

1 – 997.4 | 5 | 997.3
2/3 – 997.1 | 3

January 6th 1870

Ingots.

4 - 900 } 5
1 - 900. } 5

January 8th 1870

Toughened bar

1 - 993.6 } 8
993.7 } 8

FG B

4 - 997.4 997.5
5 - 997.4 997.5

January 10th 1870

F. G. Bar

6 - 997.3 } 5
- 997.3 } 5

January 12th 1870

F. G. bar

7/8/9 - 997.1 } 4/3
10 - 997.1

January 14th 1870

Ingots

5 - 900.2 } 5
6 - 900 } 5
- 900.4 } 5
- 900.1 } 5

7 - 899.7 } 4
8 - 899.9 } 4
- 900 } 5
- 899.9 } 5

FG Bar

11 - 997.3 } 6
997.5

January 19th 1870

F. G. Bar

1/2/3 - 997. } 3
997

January 20th 1870

FG Bars

14 - 996 } 2
15 - 996 } 2
- 996.2 } 3
- 996 } 3

January 21st 1870
F. G. Bar
16 - 996.2 | 5 | - 996.3 | 4

January 25th 1870
F. Bar
17 - 996.1 | 5 | - 996.4 | 5

January 26th 1870
18 }
19 } - 996.8 | 5 | 996.7
20 }

January 28th 1870
21 - 996 | 5 | -
T. Bar
22 - 990.1 | 5 | - 989.9 | 4

January 31st 1870
Ingot.
9 - 900.2 } - 900.1 }
10 - 899.7 } 5 - 899.5 } 1
11 - 899.7 } - 899.6 }
12 - 899.8 } - 899.8 }
13 - 899.7 } 899.5 }
14 - 899.8 } 5 899.6 } 3
15 - 899.6 } 899.5 }
9 - 900. } - 899.8 }
10 - 899.6 } - 899.2 }
11 - 899.8 } 5 - 899.8 } 4
12 - 899.81 } - 899.8 }

February 2nd 1870
F. G. Bar
23 - 996.2 | 5 | 996.3 | 6

February 2nd

Ingots.

16 – 899.8 } – 899.8 }
17 – 899.9 } 2 – 899.8 } 3
18 – 899.6 } – 899.3 }
18 – 899.4 } 899.8 } 3

F. G. Bars

25 }
6 } – 996.3 } 6
7 }

R. Assay Ingot

22 – 900. } 6 – 899.8 } 6
23 – 900. } – 900 }

February 7th 1870

Ingots.

19 – 899.9 } – 899.8 }
20 – 899.7 } 4 899.5 } 3
21 – 899.6 } – 899.5 }

F. G. Bar.

24 – 99 } 5 – 996 }

February 9th 1870

Ingots.

22 – 899.8 } – 899.7 }
23 – 900 } 7 – 899.6 } 7
24 – 900.2 } – 900 }

February 12th 1870

Toughened bars

3 – 994.5 } 5 – 994.6 } 6

February 16th 1870

F. G. Bars

28 – 996.1 } 5 – 996 3 } 5
29 }
30 } – 996.2 } 996.3 }

February 18th 1870

F. G. Bar

32 – 996.2 } 5 – 996 }

February 24th 1870
F. G. Bar
2 3 4 5 } — 996.1 | 996.2 |

February 28th 1870
F. G. Bar
36 — 996. | 996

899.8 899.9

8

8 002